

## **General Disclaimer**

### **One or more of the Following Statements may affect this Document**

- This document has been reproduced from the best copy furnished by the organizational source. It is being released in the interest of making available as much information as possible.
- This document may contain data, which exceeds the sheet parameters. It was furnished in this condition by the organizational source and is the best copy available.
- This document may contain tone-on-tone or color graphs, charts and/or pictures, which have been reproduced in black and white.
- This document is paginated as submitted by the original source.
- Portions of this document are not fully legible due to the historical nature of some of the material. However, it is the best reproduction available from the original submission.

BEHAVIOR OF  $Al_2O_3$  AND  $SiO_2$  WITH HEATING IN A  
 $Cl_2$  + CO STREAM

L. K. Shchetinin

(NASA-TM-77487) BEHAVIOR OF  $Al_2O_3$  AND  $SiO_2$   
WITH HEATING IN A  $Cl_2$  + CO STREAM (National  
Aeronautics and Space Administration) 8 p  
HC A02/MF A01 CSCL 07D

N84-33533

Unclas  
G3/25 22663

Translation of "O poved ii  $Al_2O_3$  i  $SiO_2$  pri nagrevanii v toke  
 $Cl_2$  + CO", Izvestiya vysshikh uchebnykh zavedeniy. Tsvetnaya  
metallurgiya, No. 1, 1982, pp. 43-46.



NATIONAL AERONAUTICS AND SPACE ADMINISTRATION  
WASHINGTON, D.C. 20546 JULY 1984

## STANDARD TITLE PAGE

1. Report No. NASA TM-77487	2. Government Accession No.	3. Recipient's Catalog No.	
4. Title and Subtitle BEHAVIOR OF $Al_2O_3$ AND $SiO_2$ WITH HEATING IN A $Cl_2$ + CO STREAM		5. Report Date July 1984	
		6. Performing Organization Code	
7. Author(s) L. K. Shchetinin		8. Performing Organization Report No.	
		10. Work Unit No.	
9. Performing Organization Name and Address Leo Kanner Associates Redwood City, California 94063		11. Contract or Grant No. NASW-3541	
		13. Type of Report and Period Covered  Translation	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration, Washington, D.C. 20546		14. Sponsoring Agency Code	
15. Supplementary Notes  Translation of "O povedenii $Al_2O_3$ i $SiO_2$ pri nagrevanii v toke $Cl_2$ + CO", Izvestiya vysshikh uchebnykh zavedeniy. Tsvetnaya metallurgiya, No. 1, 1982, pp. 43-46.			
16. Abstract Differential thermal analysis (DTA) and Thermogravimetric analysis (TGA) were used to study the chlorination of $\alpha-Al_2O_3$ , $\gamma-Al_2O_3$ and amorphous $SiO_2$ in a $Cl$ + CO stream, for the preparation of $AlCl_3$ and $SiCl_4$ . The chlorination starting temperatures were $235^\circ$ for $Al_2O_3$ and $680^\circ$ for $SiO_2$ . The chlorination of $\alpha$ - and $\gamma$ - $Al_2O_3$ takes place via the formation of $AlOCl$ as an intermediate product, and its subsequent dissociation at $480$ - $560^\circ$ , according to $3AlOCl \rightarrow AlCl_3 + Al_2O_3$ . The chlorination activation energies are given for the three oxides.			
17. Key Words (Selected by Author(s))		18. Distribution Statement  This copyrighted Soviet work is reproduced and sold by NTIS under license from VAAP, the Soviet copyright agency. No further copying is permitted without permission from VAAP.	
19. Security Classif. (of this report)  Unclassified	20. Security Classif. (of this page)  Unclassified	21. No. of Pages  8	22.

BEHAVIOR OF  $\text{Al}_2\text{O}_3$  AND  $\text{SiO}_2$  WITH HEATING IN A  
 $\text{Cl}_2 + \text{CO}$  STREAM

L. K. Shchetinin  
Pavlodarsk Chemical Factory

The available data in the literature on the reaction of  $\text{Al}_2\text{O}_3$  and  $\text{SiO}_2$  with a mixture of  $\text{Cl}_2 + \text{CO}$  [1-3] show their greater resistance to chlorination than for many other oxides. However, taking into account the increasing interest in aluminum and silicon chlorides, produced by chlorination of a natural raw material [4], the indicated processes are studied in more detail in the present study, with the utilization of modern physical and chemical methods. /43\*


For this purpose,  $\gamma\text{-Al}_2\text{O}_3$  and amorphous  $\text{SiO}_2$  were prepared by calcination of grade 18-1A especially pure  $\text{Al}(\text{OH})_3$  and chemically pure silicic acid at  $700^\circ \text{C}$ , as well as  $\alpha\text{-Al}_2\text{O}_3$  at  $1100^\circ \text{C}$ . The individuality of the oxides was corroborated by X-ray diffraction analysis. Chlorine and carbon monoxide were produced by well-known methods. Temperature recording was carried out on the FPK-59. The kinetics of the processes were studied utilizing McBain balances and a KM-6 cathetometer: in all cases, the weighed portion of the sample was 50 mg, the size of the oxide particles was 0.040-0.045  $\mu\text{m}$ , and the rate of heating during chlorination was  $\sim 15$  degrees/minute.

According to differential thermal analysis (DTA) and thermogravimetric analysis (TGA) of the heating of  $\alpha\text{-Al}_2\text{O}_3$  in a stream of  $\text{Cl}_2 + \text{CO}$  (Fig. 1a) and chemical analysis of the exhaust gases, the exo-effect of  $80\text{-}180^\circ \text{C}$  corresponds to the formation of phosgene. With subsequent heating, its amount decreases, which is evidently brought about by a reduction in the catalytic activity of the  $\alpha\text{-Al}_2\text{O}_3$  and dissociation of the  $\text{COCl}_2$ .

---

\*Numbers in the margin indicate pagination in the foreign text.


From the TGA curve and chemical analysis, it is evident that chlorination of the  $\alpha$ - $\text{Al}_2\text{O}_3$  begins ( $T_H$ ) at 235° C, with its interaction with phosgene, and is accompanied by the formation of  $\text{AlOCl}$



This reaction is thermodynamically possible. At 370-770° C, an endo-effect occurs on the thermogram, which is evidently brought about by the superimposed processes: additional chlorination of the  $\text{AlOCl}$ , its dissociation, and distillation of the  $\text{AlCl}_3$ :



This is indicated by the diminishing of the weight of the sample /44 being chlorinated above 480° C, and the liberation of  $\text{AlCl}_3$  vapors, beginning at 520° C. The obtained data agree with [5], where it is indicated that, up to 500° C,  $\text{AlOCl}$  is thermally stable, while at 560-570° C, it dissociates completely. With subsequent heating of the  $\alpha$ - $\text{Al}_2\text{O}_3$  in a  $\text{Cl}_2 + \text{CO}$  stream, the rate of interaction increases, and the exothermal nature of the summary process becomes preferable, as a result of the reaction



however, the degree of conversion of the oxide and chloride remains comparatively low.

The DTA curve of heating of  $\gamma$ - $\text{Al}_2\text{O}_3$  in a  $\text{Cl}_2 + \text{CO}$  stream has almost the same appearance as that for  $\alpha$ - $\text{Al}_2\text{O}_3$  (Fig. 1b). The drop in the weight of the sample, beginning at 165° C, evidently corresponds to the removal of the moisture contained in the oxide (about 0.6%). A similar process, proceeding from the analysis of the DTA curves of heating of  $\gamma$ - $\text{Al}_2\text{O}_3$  in a chloride stream and with its absence, is proposed in [6].




Fig. 1. DTA and TGA curves of heating of  $\alpha$ - $\text{Al}_2\text{O}_3$  (a),  $\gamma$ - $\text{Al}_2\text{O}_3$  (b) and  $\text{SiO}_2$  (c) in a  $\text{Cl}_2 + \text{CO}$  stream.  $\Delta m$  is the change in mass of the sample.

An appreciable interaction of  $\gamma$ - $\text{Al}_2\text{O}_3$  with  $\text{Cl}_2 + \text{CC}$  ( $\Delta m \geq 1\%$ ) begins, like in the case of  $\alpha$ - $\text{Al}_2\text{O}_3$ , at  $235^\circ \text{C}$  (Fig. 1b), and, with an increase in temperature, takes place according to the scheme (1-4). Above  $560^\circ \text{C}$  (dissociation of  $\text{AlOCl}$ ), the degree of conversion of the oxide into chloride increases sharply, which is evident from the course of the TGA curve. It was established through X-ray diffraction analysis that the oxide, which forms with dissociation of the  $\text{AlOCl}$ , undergoes conversion into  $\alpha$ - $\text{Al}_2\text{O}_3$ . The appearance of  $\alpha$ - $\text{Al}_2\text{O}_3$  lines on the X-ray diffraction pattern of the radicals from the chlorination of aluminum oxide with a  $\text{Cl}_2 + \text{CO}$  mixture above  $600^\circ \text{C}$  is also noted in study [1]. By analyzing the data in [1], the authors of [4], in the interval  $550$ - $600^\circ \text{C}$ , assume a transition of the  $\gamma$ -modification into  $\alpha$ - $\text{Al}_2\text{O}_3$ , with a simultaneous increase in the rate of the process of chlorination (so-called Hedvelli effect [7]).

It is evident from Figure 1a,b that, under equal conditions, the degree of conversion of  $\gamma$ - $\text{Al}_2\text{O}_3$  into chloride is considerably greater than for  $\alpha$ - $\text{Al}_2\text{O}_3$ . The higher activity of the  $\gamma$ - $\text{Al}_2\text{O}_3$  to chlorine is evidently brought about by the electron-donor nature of the surface of the oxide, on which, according to the data in [8], active centers ( $\text{Al}^{2+}$ ) form during the process of its dehydration, which have surplus electrons, which do not take part in /45

the valent bonds.

It is evident from analysis of the DTA and TGA curves of heating of the prepared  $\text{SiO}_2$  in a  $\text{Cl}_2 + \text{CO}$  stream (Fig. 1c) that the  $T_H$  of the interaction corresponds to  $\sim 680^\circ \text{C}$ , which is evidently accompanied by a simultaneous removal of the moisture, contained in the oxide (about 0.7%). The conversion of  $\text{SiO}_2$  into  $\text{SiCl}_4$  takes place most intensively above  $900^\circ \text{C}$ .




Fig. 2. Kinetic curves of the process of chlorination of  $\alpha\text{-Al}_2\text{O}_3$  (a),  $\gamma\text{-Al}_2\text{O}_3$  (b) and  $\text{SiO}_2$  (c) in a  $\text{Cl}_2 + \text{CO}$  stream at  $500$  (1),  $600$  (2),  $700$  (3),  $850$  (4),  $1000$  (5) and  $1150$  (6)  $^\circ \text{C}$ .

The rate of interaction with  $\text{Cl}_2 + \text{CO}$  was studied for all of these oxides. From the obtained kinetic curves of the chlorination process (Fig. 1), it is evident that the degree of conversion of  $\alpha\text{-Al}_2\text{O}_3$  and  $\gamma\text{-Al}_2\text{O}_3$  into chloride reaches 100% at  $1150^\circ \text{C}$  within 116 and 55 minutes, respectively, *i.e.*, all other conditions being equal, the weighed portion of the  $\alpha$ -modification is chlorinated nearly two times more slowly than the  $\gamma\text{-Al}_2\text{O}_3$ . As far as  $\text{SiO}_2$  is concerned, at the given temperature, it is 85% chlorinated within 2 hours. A considerable increase in the rate of interaction of the oxides with the  $\text{Cl}_2 + \text{CO}$  takes place, beginning at  $600^\circ \text{C}$ , for  $\gamma\text{-Al}_2\text{O}_3$ ,  $700^\circ \text{C}$  for  $\alpha\text{-Al}_2\text{O}_3$ , and  $850^\circ \text{C}$  for  $\text{SiO}_2$ .

The experimental data are satisfactorily described, up to the 60% degree of conversion of oxides into chlorides, by the Kolmogorov-Yerofeev equation [9]. The results of the analysis

# Results of Kinetic Analysis of Experimental Data

Chlorinated Matter	t, °C	n	K	E, $\frac{\text{kJ}}{\text{mole}}$
$\gamma\text{-Al}_2\text{O}_3$	600	2,25	0,0046	40,6
	700	2,60	0,0075	
	850	2,73	0,0090	
	1000	2,81	0,0107	
	1150	2,88	0,0166	
$\alpha\text{-Al}_2\text{O}_3$	600	1,94	0,0039	33,9
	700	2,02	0,0061	
	850	2,13	0,0084	
	1000	2,22	0,0105	
	1150	2,31	0,0131	
$\text{SiO}_2$	850	2,00	0,0025	30,5
	1000	2,05	0,0082	
	1150	2,13	0,0118	

show (table) that the processes of chlorination of  $\alpha\text{-Al}_2\text{O}_3$ ,  $\gamma\text{-Al}_2\text{O}_3$  and  $\text{SiO}_2$  have a comparatively complex nature; therefore, it is difficult to unequivocally draw a conclusion relative to the stage which limits them. The weak dependence of the rate constant on temperature, and the low /46 values of the apparent energy of activation indicate that the interaction of the oxides with  $\text{Cl}_2 + \text{CO}$  evidently occurs in the diffusion region.

Conclusions. 1. Studied herein is the chlorination of  $\alpha\text{-Al}_2\text{O}_3$ ,  $\gamma\text{-Al}_2\text{O}_3$ , and amorphous  $\text{SiO}_2$  with a mixture of  $\text{Cl}_2 + \text{CO}$ . It is established that the interaction of the modifications of oxides of aluminum begins at 235° C, and for  $\text{SiO}_2$  — 680° C.

2. It is assumed that chlorination of  $\alpha$ - and  $\gamma\text{-Al}_2\text{O}_3$  occurs via the formation of an intermediate product (aluminum oxychloride  $\text{AlOCl}$ ), with subsequent dissociation of this product at 480-560° C and polymorphous conversion of the liberated oxide into the  $\alpha$ -form.

3. Kinetic analysis of the experimental data is carried out. The values of the apparent energy of activation for the processes of chlorination of the oxides are calculated.



## REFERENCES

1. Treadvel, W., Terebesi, D., Helv. chim. Acta 15, 1053 (1932).
2. Gruner, A., Elod, D., Z. anorgan. und algem. Chem. 195, 269 (1931).
3. Polinszky, K., Ujhidy, A., Szepvolgyi, J., Hung. J. Ind. Chem. 5/2, 97 (1977).
4. Furman, A. A., Rabovskiy, B. G., Osnovy khimii i tekhnologii bezvodnykh khloridov [Bases of Chemistry and Technology of Anhydrous Chlorides], Moscow, "Khimiya" Publishers, 1970.
5. Morozov, I. S., Primenenie khloro v metallurgii redkikh i tsvetnykh metallov [Use of Chlorine in the Metallurgy of Rare and Nonferrous Metals], Moscow, "Nauka" Publishers, 1966.
6. Nechepurenko, A. V., Synopsis of Dissertation, Krasnoyarsk, 1977.
7. Hedvell, I., Z. phys. Chem. 33, 125 (1926).
8. Muzykantov, V. S., Burmakov, N. I., Vershinina, V. G., Boreskov, G. K., Kinetika i kataliz 16/2, 767 (1975).
9. Yerofeev, B. V., DAN SSSR 52, 575 (1946).